



Anti-scratch varnish SR 4

Technical data sheet

Product name: **SR 4**

Code: **1687-AO**

1. General

The SR4 varnish is a polysiloxane-based flexible coating protecting against the effects of scratching and abrasion. It is suitable for the coating of POLYAMIDES (e.g. Trogamid®), POLYCARBONATES and CR 39®.

SR4 is used without primer treatment. It can be applied by a variety of techniques followed by a cure cycle at about 75 min at 120°C or 3 h à 80°C for full reticulation.

This varnish is easily tintable with usual dyes.

2. Properties

Aspect	Colourless liquid
Content	27-31%
Density at 20°C	0.94-0.95
Viscosity at 20°C	~ 39 s. (12 mP.s - AFNOR T 30014 Cup n°2.5 – according to ISOICHEM specifications)
Shelf life*	8 months at -20 ±5 °C 4 months at +5 ±3 °C 6 weeks at +20 ±5 °C
Flash point	32°C
pH (20°C)	4.4-4.8 (according to ISOICHEM specifications)
Solvents	n-Butanol (59%), Ethanol (18%), Methanol (18%), Eau (5%)

(*) from production date and including transportation at room temperature

3. Application techniques:

- Dip,
- Flow-coating,
- Spray,
- Rotation.



4. Application process

Working place:

- Properly ventilated area
- Dust free
- Relative humidity of 30 to 50%

Preparation of the area to coat:

- Wash with a detergent solution in order to get rid of dust, fats or residue of protection
- Ultrasonic cleaning is necessary

Application :

- Varnish temperature 15-20°C
- Varnish filtration 1 micron
- Dust-free drying 20 min at 70°C in infrared channel
- Curing 120 min at 100°C (Polyamide)
75 min at 120°C (Polycarbonate)

Cleaning:

- Current cleaning : wash with n-butanol
- Deep cleaning: wash with 1% aqueous caustic soda

5. Concentration adjustment

- With n-butanol

6. Coating performance

Aspect	Clear and transparent
Refractive Index	1.5
Bayer-test	3
Colorability	Trogamid®: Excellent, Grilamid®: a primer is necessary
Adhesion	Excellent: no delamination after immersion for 30 min in boiling water

7. Packaging

1L sample and 5 kg : HDPE Jerrycan – Other upon request

8. Contact

Jean-Claude BRUYÈRE mail : jeanclaude@bruyere-pirot.com
Tél. +33 1 43 46 53 56
Mob. +33 6 82 82 05 13

The content and data presented are provided purely for information and guidance.
Controls and tests are necessary before use